



भारत का राजपत्र

The Gazette of India

प्रसारण

EXTRAORDINARY

भाग II—खण्ड 3—उपखण्ड (ii)

PART II—Section 3—Sub-section (ii)

प्रधिकार से प्रकाशित

PUBLISHED BY AUTHORITY

सं० 290] नई विल्ही, बहुस्पतिवार, सितम्बर 15, 1966/भाद्र 24, 1888
 No. 290] NEW DELHI, THURSDAY, SEPTEMBER 15, 1966/BHADRA 24, 1888

इस भाग में भिन्न पृष्ठ संख्या दी जाती है जिससे कि यह घलग संकलन के रूप में रखा जा सके।

Separate paging is given to this Part in order that it may be filed as a separate compilation.

MINISTRY OF COMMERCE

NOTIFICATION

New Delhi, the 15th September 1966

S.O. 2771.—Whereas the Central Government is of opinion that, in exercise of the powers conferred by section 6 of the Export (Quality Control and Inspection) Act, 1963 (22 of 1963), certain additional items of coir products mentioned in Annexure I to this notification should be subject to quality control and inspection prior to export, besides the items covered by the notification of the Government of India in the Ministry of Commerce No. 3918, dated the 16th December, 1965;

And whereas the Central Government has formulated the proposals specified below for the said purpose and has forwarded the same to the Export Inspection Council, as required by sub-rule (2) of rule 11 of the Export (Quality Control and Inspection) Rules, 1964.

Now, therefore, in pursuance of the said sub-rule, the Central Government hereby publishes the said proposals for the information of the public likely to be affected thereby.

2. Notice is hereby given that any person desiring to forward any objection or suggestion with respect to the said proposal may forward the same within thirty days of the date of publication of this notification to the Export Inspection Council, 'World Trade Centre', 14/1B, Ezra Street, 7th Floor, Calcutta-I.

Proposals

- (1) To notify that the said additional items of coir products shall be subject to quality control and inspection prior to export;

(2) To specify the inspection in accordance with the Export of Coir Products Inspection Rules, 1965, as amended by the draft Export of Coir Products (Inspection) Second Amendment Rules, 1966, set out in Annexure II to this notification as the type of inspection which will be applied to such coir products;

(3) To recognise—

- (a) the specifications for the said coir products as set out in Annexure III, IV and V to this notification;
- (b) specifications, as declared by the exporter provided that such specifications do not fall below the minimum prescribed for the lowest quality of the corresponding coir product specified in the said Annexures; and
- (c) the specifications other than those referred to under clause (a) or (b) but formulated by a panel of experts, appointed by the Coir Board for the purpose of examining and approving samples submitted by the exporter;

(4) To prohibit the export, in the course of international trade, of any of the aforesaid coir products unless the same is accompanied by a certificate issued by the Chairman, Coir Board, or an Officer of the Board authorised by the Chairman in this behalf to the effect that the coir products conform to the specifications recognised under sub-paragraph (3).

3. Nothing in this notification shall apply to the export by land, sea or air of samples of the aforesaid coir products to prospective buyers.

ANNEXURE I

Coir mats

- (a) Gymnasia.
- (b) Sinnet.
- (c) Corridor.

ANNEXURE II

Draft Export of Coir Products (Inspection) Second Amendment Rules, 1966

In exercise of the powers conferred by section 17 of the Export (Quality Control and Inspection) Act, 1963 (22 of 1963), the Central Government hereby makes the following rules further to amend the Export of Coir Products (Inspection) Rules, 1965, namely:—

1. These rules may be called the Export of Coir Products (Inspection) Second Amendment Rules, 1966.

2. In the Export of Coir Products (Inspection) Rules, 1965, for rule 2, the following rule shall be substituted, namely:—

“2. *Definition.*—In these rules, “Coir products” mean (i) coir door mats and

(ii) coir mats, of the following types, namely:—

- (i) *Coir door mats*
 - (a) Creel.
 - (b) Bit.
 - (c) Fibre.
 - (d) Rod.

(ii) *Coir mats*

- (a) Gymnasia.
- (b) Sinnet.
- (c) Corridor.”.

ANNEXURE III

Specification for Coir Mats for Gymnasia

1. General Requirements

1.1. Mats shall be manufactured from yarn specified in the Table below and shall be firmly and evenly woven. The pile tufts shall be secure and the cropping of the pile shall be uniform and of one level.

1.1.1. Each mat shall be bound with a braid closely plaited with 11 strands of clean, hard-twisted yarn and having a width of 30mm and the ends of the braid shall be securely fastened. The cordage used shall consist of coir rope made from hard-twisted yarn and having a circumference of 38 mm.

2. Specific Requirements.

2.1. *Construction.*—The two qualities of mats shall conform to the requirements given for each in the said Table.

NOTE.—The quality numbers in the said Table are the code names reserved by the Coir Board.

2.2. *Pile Height.*—The pile height of the finished mats shall be 60 mm. A tolerance of ± 2 mm shall be permitted.

2.3. *Dimensions.*—The dimensions of the mats shall be as agreed to between the manufacturer and the purchaser. Unless specifically agreed otherwise, a tolerance of ± 2 per cent in the dimensions shall be permitted.

2.4. *Weight.*—The weight per square meter (or square foot) of the two qualities of mats shall be within the ranges given for each in the said Table.

3. Packing

3.1. The mats shall be suitably packed, care being taken to see that the pile of the mats is not crushed while packing.

3.2. Each package shall be marked with the following particulars, namely:—

- (a) Name of material;
- (b) Size;
- (c) Number of mats packed in each package;
- (d) Code number of the exporter;
- (e) Gross weight; and
- (f) Name, initials, trade-mark, or any other identification mark of the exporter.

THE TABLE

*Constructional Details for Coir Mats for Gymnasia
(Paragraphs 1.1, 2.1 and 2.4)*

Quality Number	Pile Yarn	Weft	Warp	Weight ¹ kg/m ² (or oz/ft.)
(1)	(2)	(3)	(4)	(5)
BVGI	VYCOME Yarn un-bleached and free from impurities and pith, 4 top-pings, that is minimum three-fold yarn drawn together.	VYCOME Yarn single, sufficient to guarantee tight weave.	VYCOME Yarn, 11.0 to 11.2 (or 36 to 40)	9.8 to 11.0 (or 32 to 36)
BVGII	BEACH Yarn bleached or unbleached, 3 topplings or minimum three-fold yarn drawn together.	BEACH YARN, single, sufficient to guarantee tight weave.	VYCOME Yarn, 11.0 to 11.2 (or 36 to 40)	9.8 to 11.0 (or 32 to 36)

ANNEXURE IV

Specification for Sisal Mats

1. General Requirements

1.1. The mats shall be manufactured from plain or dyed coir-yarn braid and shall be stitched in such designs or patterns as may be specified by the buyer.

2. Specific Requirements

2.1. The constructional details of the mats of the quality numbers listed in the table shall be as specified against each in the Table below.

NOTE.—The quality numbers in the said Table are the code names reserved by the Coir Board. Unless specifically agreed otherwise, a tolerance of \pm 2 per cent shall be permissible.

2.2. *Dimensions.*—The dimensions of the mats shall be as specified by the buyer. Unless specifically agreed otherwise, a tolerance of \pm 2 per cent shall be permissible.

2.3. *Weight.*—The weight per square metre (or square foot) of the mats of the quality numbers listed in the said Table shall be in accordance with the relevant requirements in the said Table. A tolerance of \pm 5 per cent on the weight shall be permitted.

3. Packing

3.1. The mats shall be packed as agreed to between the buyer and the seller.

3.2. Each package shall be marked with the following particulars, namely:—

- (a) Name of material;
- (b) Size;
- (c) Number of mats packed in each package;
- (d) Code number of the exporter;
- (e) Gross weight; and
- (f) Name, initials, trade-mark, or any other identification mark of the exporter.

THE TABLE

Constructional Details of Sinnet Mats

(Paragraphs 2.1 and 2.3)

Quality Number (1)	Material		Braid			Weight	
	Quality of Yarn (2)	Scorange Min. (3)	No. of strands of ply (4)	Thickness mm (5)	Thickness in. (6)	kg/m ² (7)	oz/dft. ² (8)
SA1 . . . Anjengo		12	9	19	0.75	3.65	12
SA2 . . . "		12	9	19	0.75	4.25	14
SA3 . . . "		12	11	25	1.00	4.85	16
SA4 . . . "		12	11	25	1.00	5.45	18
SA5 . . . "		12	11	25	1.00	6.10	20
SRI . . . Aratory		12	9	19	0.75	3.35	11
SR2 . . . "		12	9	19	0.75	3.95	12
SR3 . . . "		12	11	25	1.00	4.60	15
SR4 . . . "		12	11	25	1.00	5.20	17
SR5 . . . "		12	11	25	1.00	5.80	19
SV1 . . . Vycome		11	9	19	0.75	3.65	13
SV2 . . . "		11	9	19	0.75	4.25	14
SV3 . . . "		11	11	25	1.00	4.85	16
SV4 . . . "		11	11	25	1.00	5.45	18
SBI . . . Beach		...	9	19	0.75	3.85	12
SB2 . . . "		...	9	19	0.75	3.95	12
SB3 . . . "		...	11	25	1.00	4.60	13

NOTE.—Coir yarn for the inner strands of the braid may be of a suitable quality.

ANNEXURE V

Specification for Corridor Mats

1. General Requirements

1.1. The mats shall be firmly and evenly woven.

1.1.1. The mats may be supplied plain or dyed or with simple designs as may be specified by the buyer.

1.1.2. The mats shall be free from extraneous matter and salt.

2. Specific Requirements

2.1. *Construction.*—The mats shall conform to the constructional details given in the Table below.

2.2. *Dimensions.*—The Dimensions of the mats shall be as specified by the buyer. Unless specifically agreed otherwise, a tolerance of \pm 2 per cent in Dimensions shall be permissible.

2.3. *Ends.*—The minimum number of ends per decimetre (or foot) of the mats listed in the said Table shall be in accordance with the requirements indicated in that Table against each.

2.4. *Weight.*—The weight per square metre (or square foot) of corridor mats shall be as specified in the said Table. A tolerance of \pm per cent on the weight so specified shall be permitted.

3. Packing

3.1. The mats shall be packed as agreed to between the buyer and the seller.

3.2. Each package shall be marked with the following particulars, namely:—

- (a) Name of material;
- (b) Size;
- (c) Number of mats packed in each package;
- (d) Code number of the exporter;
- (e) Gross weight; and
- (f) Name, initials, trade-mark, or any other identification mark of the exporter.

THE TABLE
Constructional Details of Corridor Mat.
 (Paragraphs 2.1, 2.3 and 2.4)

Quality Number (1)	Warp		Weft		Weight in kg/m ² (or oz/ft ²) (6)
	Quality of yarn (2)	Ends per dm (or per foot), Min. (3)	Quality of yarn (4)	Scorgae Min. (5)	
AC ₁	Rope yarn	6(or 18/19)	Angengo	13	4.55(or 15)
AC ₂	"	5(or 14/15)	"	13	4.25(or 14)
AC ₃	"	5(or 14/15)	"	12	3.65(or 12)
RC ₁	"	6(or 18/19)	Aratory	13	4.25(or 14)
RC ₂	"	5(or 14/15)	"	13	4.00(or 13)
RC ₃	"	5(or 14/15)	"	12	3.35(or 11)
LC ₁	"	5(or 14/15)	Alapat	12	4.25(or 14)
WC ₁	"	5(or 14/15)	Vycome	13	4.25(or 14)
WC ₂	"	5(or 15/16)	"	12	3.65(or 12)
WC ₃	"	5(or 14/15)	"	11	3.05(or 10)
TC ₁	"	5(or 14/15)	T. Vycome	..	3.65(or 12)
IC ₁	"	5(or 15/16)	Beach	..	3.05(or 10)

[No. 60(4)Exp.Insp/63P.II.]
 A. C. BANERJEE, Jt. Secy.

